



REF : RS69 2013 07

Resuthane RS69

DESCRIPTION

Resuthane RS69 is a water-based polyurethane resin screed designed to provide excellent heavy duty usage with resistance to thermal shock, abrasion and chemical attack in many aggressive environments.

RS69 and RSC90 grades are designed to be applied by use of rake and trowel methods of application.

Resuthane surfaces are stable to steam cleaning and resistant to boiling water and process liquids up to 120°C when applied at 9mm nominal thickness. A matt, textured surface is provided that is both seamless and possesses good anti-slip properties.

ADVANTAGES

- High chemical resistance
- Resistant to hot water & steam water
- Excellent slip resistant finish
- Extremely hard wearing
- Food Safe & non taint (Campden BRI Approved)
- Extremely Hard Wearing

RECOMMENDED USES

- Food manufacture & processing
- Brewing & beverage
- Dairies
- Commercial kitchens
- Pharmaceutical & chemical plant processing
- Abattoirs
- Heavy duty plant and traffic areas

PRODUCT INFORMATION

System thickness (dry)	Solids content	Pack sizes	Pack make up	Shelf life	Storage
6mm to 9mm	100%	26 Kg.	1 X Base 1 X Hardener 1 X Aggregate	12 Months (Base & Hardener) 3 Months (Aggregates)	Keep out of direct sunlight. Store in a dry place, not below 15°C

DRYING TIMES & COVERAGE RATES at 20°C

Coverage rate	Pot life	Recoat time	Light traffic	Full traffic	Full chemical cure
26 kg. will cover 2.0 sq m @ 6mm or 1.35 sq m @ 9mm	15 minutes (From Mixing)	N/A	12-16 Hours	48 Hours	3 - 5 Days



Specification

Product : Resuthane RS69

Finish : Textured, Matt Finish

Thickness : 6mm or 9mm

Colour : See RSL Resuthane Colour Chart

Products required for this system

Prime : Resuprime /R.S. Dampshield

System : Resuthane RS69 at required Thickness

Surface Seal : Not required

NB: All polyurethane systems based on MDI will yellow with time this is a surface discolouration under the effect of UV light and does not in any way affect the durability of the floor finish. Darker colours will not show this effect as much as light colours.

Preparation

To achieve the best performance from **Resuthane RS69** the correct surface preparation is essential. Substrates must be clean, sound, dry and free of surface laitance with a minimum strength of 25N/mm². All surfaces must be prepared by vacuum blasting or mechanical abrasion.

Resuthane RS69 may be applied to substrates with a surface temperature in the range of 5-20°C and a relative humidity < 90% RH, with a minimum air temperature of 8°C and no condensation. Do not prework this product as it will adversely affect working time and finish. Do not pre-warm this product as working times will be substantially reduced if materials are warm.

To ensure the maximum bond is achieved, grooves must be cut into the perimeter of the subfloor, typically 20mm deep by 8mm wide. These should be inset approximately 150mm from, and running parallel with the walls and adjacent to any doorways, plinths etc. including any finished edge, i.e. both sides of a daywork joint. The groove must have a neat square edge and the **Resuthane RS69** laid to the full depth forming a perimeter anchorage.

Priming

Surfaces should be primed with **Resuprime** at an average rate of 4 sq.m. per kg. **R.S. Dampshield** should be applied if the relative humidity of the concrete is greater than 75% RH at 4 sq.m. per kg, allow to cure for 8-12 hours @ 20°C.

Application

When the primed surface is tack free **Resuthane RS69** should be applied at the required rate as soon after mixing as possible. (Delay can result in variation in surface finish, colour and cause application problems.)

Mix the coloured base component to an even consistency, ensuring the re-dispersion of any settled pigment, Thoroughly scrape the contents of the base and hardener components into the same container and mix thoroughly for one minute. Pour the combined base and hardener into a rotary drum mixer and add the aggregate component steadily, until a homogeneous mix of the three components is achieved. Apply to pre-primed areas and level between battens with a steel trowel or rake as necessary, alternatively a sledge can be used set at the required thickness and again finished with a steel float. Where ease of cleaning is very important alongside slip resistance the final finish can be smoothed by back rolling with a short nap roller. A single pass with the weight of the roller is usually sufficient.

Resuthane RS69 units should be applied consistently with mixes from the same batch used consecutively where adjacent areas are being laid.

NB: Cure times are extended at low temperatures.

Category Guide

FerFA Category : 8

Technical Information

The following figures are obtained from laboratory tests and our

Slip Resistance Dry > 50, low slip potential
Method BS7976 pt1-3 2002 Wet > 45, low slip potential

The slip resistance of a floor surface can vary as a result of the installation process, conditions at the time of application and subsequent traffic. Inappropriate cleaning or maintenance can adversely affect the performance. For further advice on potential wet areas please consult RSL.

Abrasion Resistance Average Depth of Wear (mm)
Method BS8204 /ASTM D4060 0.04

Temperature Resistance Tolerant of sustained
temperatures of up to 120°C @ 9mm

Chemical Resistance Excellent Chemical Resistance
Consult RSL on specific materials

Compressive Strength 60N/mm²

Flexural Strength 14N/mm²

Tensile Strength 6N/mm²

Reaction to fire classification BFL - S1
EN 13501-1:2007+A1: 2009.

VOC 9g/l
Calculation based on a full mixed unit

Life Expectancy 10 years plus
Subjected to Industrial Traffic
RSL terms and conditions will apply



Resin Surfaces Ltd

Titan House, Lowick Close, Newby Road Industrial Estate
Hazel Grove, Stockport. SK7 5ED

13

BSEN 13813 SR B 3.2 - AR 0.5 - IR>4

Resin coating/screed for use inside buildings as per RSL data sheet

Wear resistance: AR 0.5

Bond strength: B 3.2

Impact resistance: IR > 4

Maintenance and Cleaning

RSL recommend that **Resuthane RS69** should be cleaned with a regular industrial cleaning regime with a floor scrubber utilising **R.S. Industrial Floor Cleaner** or similar with dirty water being removed. Isolated localised cleaning can be carried out using **R.S. Tyre Mark Remover**, **R.S. Fats & Grease Remover** & **R.S. Oil Remover**.

All surfaces should be thoroughly rinsed with clean water after the use of chemical cleaners.

Please refer to RSL Data Sheet CLNG for Cleaning Advice

Health and Safety

Resuthane RS69 is formulated from materials designed to achieve the highest level of performance as safely as possible. However, specific components require proper handling and suitable equipment, this information is given in the relevant safety data sheets. In all cases, spillages or skin contamination should be cleaned as soon as practically possible, by dry wiping of the affected area, and thorough washing with soap and water.

The information given in this data sheet is derived from tests and experience with the products and is believed to be reliable. The information is offered without guarantee to enable purchasers to determine for themselves the suitability of the product for their particular application. Any specification or advice given by Resin Surfaces Limited or its agents is based on the information supplied by the purchaser. Resin Surfaces Limited cannot be held accountable for errors or omissions as a result of that information being incorrect or incomplete. No undertakings can be given against infringement of patents. Some materials are derived from natural sources. As such some variation may occur. Site conditions may also contribute to variation in finish and colour.

Tel : + 44 (0) 161 483 1232 Fax: + 44 (0) 161 483 2565
Email : info@resinsurfaces.co.uk Web : www.resinsurfaces.co.uk
Registered in England : 1659941 Vat No : GB 373 485 624